

# MARMOSMART

GRANITOKER



CASALGRANDE  
PADANA  
Pave your way

## CARATTERISTICHE TECNICHE TECHNICAL FEATURES

## CARACTÉRISTIQUES TECHNIQUES TECHNISCHE EIGENSCHAFTEN



NORMA STANDARDS  
NORME NORM

RISULTATO PROVA\* TEST RESULTS\*  
RESULTATS DES ESSAIS\* ERGEBNISSE\*

	Classificazione prodotto Product classification Classement Klassifizierung	UNI EN 14411-G ISO 13006	Gruppo Bla GL completamente greificato Group Bla GL fully vitrified Group Bla GL grès cérame fin Gruppe Bla GL Feinsteinzeug
	Caratteristiche dimensionali e d'aspetto Dimensional and surface quality Caractéristiques de la surface Oberflächenqualität	UNI EN ISO 10545-2	Tolleranze minime nella 1ª scelta Very low tolerance Des tolérances minimes en 1er choix Entspricht Normen
	Assorbimento di acqua Water absorption Absorption d'eau Wasseraufnahme	UNI EN ISO 10545-3	< 0,1%
	Resistenza alla flessione Flexural strength Résistance à la flexion Biegezug-Festigkeit	UNI EN ISO 10545-4	> 45 N/mm <sup>2</sup>
	Resistenza al gelo Frost resistance Résistance au gel Frostwiderstandsfähigkeit	Qualsiasi norma All standards Toute norme Alle normen	Garantita Guaranteed Garantie Frostsicher
	Resistenza attacco chimico (esclusione acido fluoridrico) Resistance to acids and alkalis (with the exception of hydrofluoric acid) Résistance à l'attaque chimique (exclusion de l'acide fluorhydrique) Säure und Laugen Beständigkeit (mit Ausnahme von Fluorwasserstoff)	UNI EN ISO 10545-13	GA
	Resistenza usura e abrasione Wear and abrasion resistance Résistance à l'usure et abrasion Abriebhärte	UNI EN ISO 10545-6	≤ 150 mm <sup>3</sup>
	Dilatazione termica lineare Linear thermal expansion Coefficient linéaire de dilatation thermique Lineare Wärmeausdehnung	UNI EN ISO 10545-8	6 x 10 <sup>-6</sup>
	Resistenza alle macchie Stain resistance Résistance aux taches Fleckenfestigkeit	UNI EN ISO 10545-14	Garantita Guaranteed Garantie Garantiert
	Resistenza alla scivolosità Slip resistance Résistance au glissement Trittsicherheit	DIN 51130	<b>R10 A+B</b> <b>R10 HONED</b>
		D.M. N° 236 del 14.06.89 Metodo B.C.R.	Valore $\mu > 0,40^*$
		BS7976-2:2002 BSEN13036-4:2011	PTV > 36**
	Resistenza dei colori alla luce Colour resistance to sunlight exposure Résistance de la couleur à la lumière Unveränderlichkeit der Farben wenn Strahlung zugesetzt wird	DIN 51094	Nessuna variazione No change of colours Couleurs inchangées Keinerlei Farbänderung

\* Valore indicativo Approx value Donnée approximative Ungefähre Werte

\*\* Prova su superficie asciutta Test on a dry surface Essai sur surface sèche Test auf trockener Oberfläche

◆ Si rimanda all'elenco prodotti UPEC ufficiale, consultabile sul sito: Please see the official UPEC product list:

Veuillez consulter la liste officielle produits UPEC: Sihe die offizielle UPEC-Produktliste auf der Website: <http://webapp.cstb.fr/upec-ceramique/>